

1930

A Study of Phosphorescent Zinc Sulphide Screens and Radioactivity Under Extremely High Pressure

Thomas C. Poulter
Iowa Wesleyan College

Harold McComb
Iowa Wesleyan College

Let us know how access to this document benefits you

Copyright ©1930 Iowa Academy of Science, Inc.

Follow this and additional works at: <https://scholarworks.uni.edu/pias>

Recommended Citation

Poulter, Thomas C. and McComb, Harold (1930) "A Study of Phosphorescent Zinc Sulphide Screens and Radioactivity Under Extremely High Pressure," *Proceedings of the Iowa Academy of Science*, 37(1), 311-312.

Available at: <https://scholarworks.uni.edu/pias/vol37/iss1/78>

This Research is brought to you for free and open access by the Iowa Academy of Science at UNI ScholarWorks. It has been accepted for inclusion in Proceedings of the Iowa Academy of Science by an authorized editor of UNI ScholarWorks. For more information, please contact scholarworks@uni.edu.

The same discrepancy has been found between the spectrophotometric readings for the meat and the Color Chart which matched it as was previously observed between the readings of the meat and the Munsell Color Disc. But with the Charts the total amount of light diffusely reflected was greater than that from the meat, whereas that from the Disc was less.

IOWA STATE COLLEGE,
AMES, IOWA.

A STUDY OF PHOSPHORESCENT ZINC SULPHIDE
SCREENS AND RADIOACTIVITY UNDER EX-
TREMELY HIGH PRESSURE

THOMAS C. POULTER AND HAROLD MCCOMB

For a study of the effect of pressure on fluorescent zinc sulphide screens, an arrangement very similar to that used in the preceding paper was employed. In this case the fluorescent zinc sulphide was mounted on the inner surface of the pressure window with a transparent cement.

The pressure was applied to the oil surrounding the screen and the screen illuminated with a 100 watt bulb placed 30 cm. from the screen.

The light was turned out and the phosphorescent glow of the screen observed with a spectroscope.

This procedure was repeated for pressures ranging from one to twenty thousand atmospheres and very little if any effect was observed except that the intensity of the phosphorescence was less at the higher pressures.

However, in all cases where the pressure was rapidly decreased, a very marked increase in the intensity (perhaps two to five fold change) was observed. The intensity immediately dropped to its normal value as soon as the pressure was brought to a constant value.

A similar arrangement was then used in which case the window was coated over one half the field on the inner surface and exposed to the oil pressure while the other half of the window was coated on the outer surface.

In this case the decrease in intensity at higher pressures was made very apparent as was the sudden increase in intensity as the pressure was rapidly lowered.

Since fluorescent screens are effected so little by pressures up to

20,000 atmospheres and this offered such a convenient method for observing radioactivity, a spintharoscope arrangement was set up by using a florescent zinc sulphide screen containing a small amount of radium. This was mounted on the inner surface of the pressure window and a microscope focused on this screen, so that the scintillations could be observed.

Observations were made as the pressure was changed from one to twenty thousand atmospheres. For observations of this kind no attempts have been made as yet to make an actual count of scintillations at various pressures but so far as we could tell, the number of scintillations was unaffected as the pressure was changed.

CONCLUSIONS

1. The intensity of the phosphorescence of zinc sulphide screen is decidedly less (perhaps one-half) under extremely high pressures.
2. Aside from the intensity, the florescent and phosphorescent properties of zinc sulphide are very little affected by extremely high pressures.
3. Radioactivity is affected very slightly if at all by pressures as high as 20,000 atmospheres.

IOWA WESLEYAN COLLEGE,
MT. PLEASANT, IOWA.

APPARATUS FOR DETERMINATION OF RESISTIVITY AT LOW TEMPERATURES

A. G. HOYEM

An apparatus has been designed following the method of Cioffi and Taylor (J. O. S. A. and R. S. T. 6, 906 (1922)), by which the resistance of 2 single crystal specimens can be determined simultaneously at temperatures ranging from liquid air to room temperature. The method is being used to investigate crystals of "spectroscopically pure" zinc.

STATE UNIVERSITY OF IOWA,
IOWA CITY, IOWA.

MAGNETIZATION OF ELECTROLYTIC NICKEL FILMS

E. P. T. TYNDALL AND H. E. MALMSTROM

The magnetic properties of nickle films electrolytically deposited on brass tubes are determined by the method previously described